

Facestock

A white, one side machine coated, woodfree printing paper with semi-gloss appearance.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	88 g/m ²	ISO 536
Caliper	76 µm	ISO 534

Adhesive

A general purpose removable, rubber based adhesive.

Liner

BG40 brown, supercalendered glassine paper.

Basis Weight	53 g/m ²	ISO 536
Caliper	46 µm	ISO 534

Laminate

Total Caliper	144 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	2.5 N/25mm	FTM 9 Glass
Peel Adhesion 90°	1.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	-20 °C	
Service Temperature	-40 °C to 80 °C	

Adhesive Performance

The adhesive is suitable for general application on a wide range of substrates, featuring good initial tack and adhesion combined with excellent removability. In addition the adhesive has superb low temperature performance.
Remark: Application to porous substrates such as paper and board, or prolonged exposure to UV light may adversely affect clean removability. Removable adhesive, by nature, have a low cohesion and might be subject to variation in the product aesthetics which could be observed on the web rolls as long as the material is not used. We recommend to store the material with the inner core in vertical position after delivery.

Applications and Use

The product is suitable for a wide range of promotional and industrial label applications where attractive semi-gloss appearance in multi-colour work is required.

R100 removes clean from many substrates from polymeric (PET, PP, ABS, PS), greeting cards, aluminium, stainless steel and glass (not suitable for window labelling)

Conversion and Printing

Facestock is suitable for solid and halftone images and text printing by letterpress, flexo (UV and waterbased) offset and screen processes. Hot and cold foil stamping, varnishing and variable imprinting with thermal transfer are also suitable for this product.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AA020

Fasson ®

MC90 FSC
R100-BG40BR IMP



MC90 FSC

R100

BG40BR



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.