

Facestock

A matt, white woodfree machine finished paper with blue backcoating, providing very good absorption and toner bonding characteristics.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	95 g/m²	ISO 536
Caliper	90 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

Hygroflat 55, a one side coated, bleached kraft paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	55 g/m²	ISO 536
Caliper	58 µm	ISO 534
Laminate		
Total Caliper	164 µm±10%	ISO 534
Performance Data		
Initial Tack	17 N/25mm	FTM 9 Glass
Peel Adhesion 90°	7 N/25mm	FTM 2 St.St.
Min. Application Temp.	0°C	
Service Temperature	-20 °C to 80 °C	;

Adhesive Performance

The adhesive is characterized by a high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates.

Applications and Use

This face material is designed for the manufacture of A4 sheets for use in laserprinters, copiers and monochrome inkjet printer. The surface structure provides very good toner bonding and print resolution. Applications are labels where high opacity is important such as office labels for error correction or to cover-up obsolete information.

The hygroflat backing paper is specially suited to the more critical refanfolding demands of high-speed computer printers, providing optimum layflatness and excellent interfolding characteristics.

Conversion and Printing

Facestock is suitable for simple line or process printing by flexo and offset. The material can be converted by the conventional roll-to-sheet conversion technologies.

The Backing paper can be printed with conventional printing methods.


Compliance and Approvals

The adhesive S2012HTC is suitable for contact with dry, moist, and fatty foodstuffs that have a reduction factor of 4 or higher in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

AA186

Fasson ®

LCJ PREMIUM OPQ FSC S2012HTC-HF55 FSC



LCJ PREMIUM OPQ FSC

S2012HTC

HF55 FSC



The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



The laminate is made with FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.