

#### **Facestock**

A white machine coated, supercalendered woodfree printing paper with semi gloss finish.

Basis Weight 25 g/m² ISO 536
Caliper 33 µm ISO 534
Fluorescence >9 Laetus Scale

#### Adhesive

A special purpose permanent, acrylic based adhesive for direct food contact.

#### Liner

BG40 BROWN FSC certified, supercalendered glassine paper. The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight 54 g/m² ISO 536 Caliper 47 µm ISO 534

#### Laminate

Total Caliper 100 µm±10% ISO 534

#### Performance Data

Initial Tack 8 N/25mm FTM 9 Glass Peel Adhesion 90° 5.5 N/25mm FTM 2 St.St.

Min. Application Temp. -15 °C

Service Temperature -50 °C to 80 °C

#### Applications and Use

The flexible facestock allows application on small cylindrical containers, test tubes, curved substrates and on other known substrates in the pharmaceutical industry. The luminescent properties of the product allow automatic label dispensing and/or missing label control using UV-light detection equipment.

## Conversion and Printing

Excellent conversion characteristics in rotary and flat-bed. The double coated flexible paper allows fine-quality printing in letterpress, offset, flexo, screen, hot foil stamping and permits high quality printing of small typeface and difficult characters with optimum results

#### Compliance and Approvals

The adhesive used in this construction may be used in direct food contact applications. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.


### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

# **AA495**

# Fasson ®

BT25 S2800-BG40BR FSC



LW FSC	
--------	--

S2800	3/3/3/





The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



## Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty
All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <a href="http://terms.europe.averydennison.com">http://terms.europe.averydennison.com</a>



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.