

### Facestock

A white monomeric, plasticised PVC film.

Basis Weight	112 g/m <sup>2</sup>	ISO 536
Caliper	84 µm	ISO 534

### Adhesive

A special purpose extra permanent, rubber based adhesive.

### Liner

HF140, a one side coated, bleached kraft paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	135 g/m <sup>2</sup>	ISO 536
Caliper	142 µm	ISO 534
Transparency	94 %	DIN 63147

### Laminate

Total Caliper	248 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	20 N/25mm	FTM 9 Glass
Peel Adhesion 90°	12 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 80 °C	

### Adhesive Performance

S277 is an highly aggressive permanent adhesive with excellent tack and adhesion to a wide variety of substrates including rough and apolar substrates.NB. Due to the nature of the adhesive, a slight yellowing effect of the adhesive may occur over time.

### Applications and Use

Applications are predominantly in industrial and chemicals for indoor use offering good durability. Further applications include labels on plastic bottles for household chemicals and motor oil.

The hygroflat backing paper is specially suited to the more critical refanfolding demands of high-speed computer printers, providing optimum layflatness and excellent interfolding characteristics.

### Conversion and Printing

The corona treated face material can be printed by conventional printing techniques including flexo, screen, offset, letterpress, silkscreen, gravure, and hot or cold foiling processes. UV, water-based and solvent-based inks can be used. On-press corona treatment is recommended for optimum ink adhesion. We strongly recommend to use a primer in the printing process of PVC in general. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier.

### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

# AA683

## Fasson ®

### PVC WHITE S277-HF140 FSC



PVC WHITE

S277

HF140 FSC



The mark of  
responsible forestry

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

## Appendix

### Compliance with BS 5609

This material complies with BS 5609, Section two, Marine Immersion Test.

## Thermal Transfer Printing:

### Printability – Physical Resistance

Ribbon	Settings speed energy		Print Quality	ANSI Grade	Scratch resistance	Tape resistance
Armor AXR7+	5	20	++	A	++	++
Armor AXR8	5	30	++	A	++	+
DNP R300	5	30	++	B	++	++
DNP R510	5	20	++	A	++	++
DNP R550	5	30	+	A	++	++
limak PM255	5	30	+	A	-	-
limak SP330	5	30	o	A	++	+
Ricoh B110A-X2	5	20	++	A	-	o
Ricoh B120EC	5	30	-	F	-	+
Ricoh B110CR	5	30	++	A	++	++

ANSI (American National Standards Institute) Grade: information about barcode quality

A: excellent B: good C: acceptable D: readable with difficulty

++: excellent +: good o: acceptable -: poor

Tests were performed with the printer Zebra 140XI3.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.