

Facestock

A clear corona-pretreated polypropylene film featuring an appealingly tactile surface.

Basis Weight 57 g/m 2 ISO 536 Caliper 65 μm ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG40 white, a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight 57 g/m^2 ISO 536 Caliper $51 \mu \text{m}$ ISO 534

Laminate

Total Caliper 134 µm±10% ISO 534

Performance Data

Initial Tack 10 N/25mm FTM 9 Glass Peel Adhesion 90° 6 N/25mm FTM 2 St.St.

Min. Application Temp. 5 °C

Service Temperature -20 °C to 80 °C

Adhesive Performance

S692N is a clear permanent adhesive featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates.

Applications and Use

Applications include labelling of quality products such as cosmetics, toiletries, luxury articles and promotional labelling.

Conversion and Printing

The film can be printed by all conventional printing processes. Consult your printing ink manufacturer or supplier about suitable printing inks. Corona pre-treatment is required prior to printing.

Compliance and Approvals

The adhesive S692N is suitable for contact with dry, moist and fatty foodstuffs with a reduction factor of 3 or higher in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.


Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AB289

Fasson ®

PP SOFT TOUCH S692N-BG40WH FSC



PP SOFT TOUCH

S692N

BG40WH FSC



The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty
All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.