

Facestock

A gloss white polyester film with 'print treated' surface for enhanced ink adhesion.

 $\begin{array}{lll} \text{Basis Weight} & 71 \text{ g/m}^2 & \text{ISO } 536 \\ \text{Caliper} & 50 \text{ } \mu\text{m} & \text{ISO } 534 \\ \end{array}$

Adhesive

A special purpose permanent, acrylic based adhesive.

Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight 69 g/m^2 ISO 536 Caliper $60 \text{ } \mu \text{m}$ ISO 534

Laminate

Total Caliper 125 µm±10% ISO 534

Performance Data

Initial Tack 12 N/25mm FTM 9 Glass Peel Adhesion 90° 6.5 N/25mm FTM 2 St.St.

Min. Application Temp. 10 °C

Service Temperature -20 °C to 80 °C

Applications and Use

Durable applications where heat and solvent resistance are required.

Conversion and Printing

The print treated face can be printed by letterpress, flexo, gravure and screen giving good print results with solvent, UV curing and water-based inks. Corona treatment is recommended for optimum print results; Care should be taken in selection of waterbased and UV screen inks. Product is Thermal Transfer printable.


Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AB708

Fasson ®

PET50 PT WHITE S695 DEC-BG45WH FSC



PET50 PT WHITE

S695

BG45WH FSC



The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty
All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.