

### Facestock

A bi-axially oriented bright shimmer design holographic polypropylene film with topcoat, laminated to paper. The holographic facestock contains aluminium and the metallised side remains inside the lamination film+ paper.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	70 g/m <sup>2</sup>	ISO 536
Caliper	60 µm	ISO 534

### Adhesive

A general purpose permanent, acrylic based adhesive.

### Liner

BG40 BROWN FSC certified, supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	54 g/m <sup>2</sup>	ISO 536
Caliper	47 µm	ISO 534

### Laminate

Total Caliper	126 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	16 N/25mm	FTM 9 Glass
Peel Adhesion 90°	9 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 80 °C	

### Adhesive Performance

The adhesive is characterized by a high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates.

### Applications and Use

Holographic labels are particularly eye catching and give brands an extra chance to catch the customer's attention, on very competitive markets. Traditionally used in cosmetics, they fit also Spirits and trendy beverages.

### Conversion and Printing

The film can be printed by conventional printing techniques including Gravure, UV flexo and offset. For optimum ink adhesion a primer is advised and corona treatment recommended. Please consult your ink supplier for ink recommendations. In circumstances where high scuff resistance is required, over varnish or over lamination of the printed labels is advised. The pattern range is made by cliches of different dimensions, therefore some lines can appear on the hologram. A shimline will appear, in cross-direction every 733mm +/- 5mm.

### Compliance and Approvals

The adhesive S2000N is suitable for contact with dry, moist, and fatty foodstuffs that have a reduction factor of 4 or higher in this construction in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

## AB709

## Fasson ®

### HGFP SHIMMER TOP FSC S2000N-BG40BR FSC



HGFP SHIMMER TOP FSC

S2000N

BG40BR FSC



The mark of  
responsible forestry

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

The laminate is made with FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

#### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

#### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see

<http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.