

Facestock

A gloss white polyester film. The smooth surface is covered with a topcoat for very good ink anchorage.

Basis Weight	76 g/m ²	ISO 536
Caliper	50 µm	ISO 534

Adhesive

S8030 is a high strength permanent solvent based acrylic adhesive.

Liner

BG42 white, a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	63 g/m ²	ISO 536
Caliper	56 µm	ISO 534
Transparency	50 %	DIN 53147

Laminate

Total Caliper	130 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	16 N/25mm	FTM 9 Glass
Peel Adhesion 90°	12 N/25mm	FTM2 st.st.
Min. Application Temp.	7 °C	
Service Temperature	-40 °C to 150 °C	
Adhesive Coat Weight	24 g/m ²	FTM12
Adhesive Type	Solvent Acrylic	

Adhesive Performance

S8030 features a balanced adhesive performance on a wide variety of substrates including low energy plastics combined with good chemical resistance.

Applications and Use

Transfer PET white TOP is designed for conversion into identification, warning and tracking labels for durable goods such as automotive parts, electronic devices and home appliances. This product is distinguished by the high chemical resistance of the thermal transfer print. For special requirements we strongly recommend application tests.

This all-round performing product provides good adhesion onto low surface energy plastics combined with the long term durability expected from a solvent acrylic adhesive.

Conversion and Printing

Very good results can be achieved with thermal transfer printers equipped with conventional or near-edge print heads using resin ribbons. Transfer PET white TOP can also be printed by all conventional roll label techniques, including flexo, UV letterpress, silkscreen. This material is qualified for UV inkjet printing by the following printer manufacturers: EFI Jetrion, Domino (n610i), Durst (TAU 330 RSC) and Xeikon (PX3000). Results of durability tests are available on request. For easy diecutting sharp corners should be avoided.

AD222

Fasson®

TRANSFER PET WHITE TOP S8030-BG42WH FSC



TRANSFER PET WHITE TOP

S8030

BG42WH FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Compliance and Approvals

Sustainable alternative: This material is available with 70% recycled content in the face material under a *different product code*.

This product is UL and C-UL recognized (UL 969, CSA C22.2 No. 0.15). The UL file number is MH27538.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Appendix

UL and CSA recognition

This product meets the requirements as stated in UL 969 and CSA C22.2 No. 0.15 for indoor use. The UL file number is MH27538. For specific information on approved conditions, see appendix.

Performance Data

Note: the following technical data should be considered representative or typical only and should not be used for specification purposes.

Peel Adhesion:

FTM1: 180°, 300 mm/min, dwell time: 48 hours

Surface	N/25mm
ABS	13,0
Aluminium	13,0
Automotive lacquered panels	14,0
Glass	14,5
HDPE	10,0
LDPE	8,0
PA6	13,0
Stainless Steel	15,0

Chemical Resistance:

The performance results are based on 4 hours immersions at room temperature unless otherwise noted. Samples were applied to the test panel and conditioned for 24 hours before immersion and evaluated immediately upon removal. Peel adhesion was measured according to FTM1.

Chemical	Test Substrate	N/25mm	Visual appearance	Edge Penetration
Ad Blue	Aluminium	14,0	No change	0 mm
Biodiesel	Glass	13,9	No change	0 mm
Bioethanol E85	Glass	13,1	No change	2 mm
Brake Fluid	Glass	12,0	No change	0 mm
Diesel	Glass	13,0	No change	0 mm
Engine Oil	Glass	12,5	No change	0 mm
Gasoline	Glass	9,0	No change	4 mm
Heptane	Glass	8,0	No change	4 mm
Water, distilled	Aluminium	10,0	No change	0 mm

Chemicals:

Ad Blue: Aral, Bioethanol E85: CropEnergies CropPower85, Brake Fluid: DOT 4 Synthetic (One Way)
Diesel: TOTAL, Engine Oil: TOTAL quartz 700, 10 W 40, Gasoline: TOTAL Euro 95

Appendix

Thermal Transfer Printing:

Printability – Physical Resistance

Flat head printers (tests were performed with the printer Zebra XII 140):

Ribbon	Settings speed energy		Print Quality	ANSI Grade	Scratch resistance	Tape resistance
Armor AXR7+	3	20	++	A	++	++
Armor AXR8	3	15	++	A	++	++
DNP R300	3	15	++	A	++	++
DNP R510	3	20	++	A	++	++
limak SP330	3	15	++	A	++	++
ITW B324	3	15	++	A	++	++
Ricoh B110CR	3	15	++	A	++	++
Zebra 4800	3	20	++	A	++	++
Zebra 5095	3	15	++	A	++	++

Near edge printers (tests were performed with the printer Avery TTX 450 – Near Edge):

Ribbon	Settings	Print Quality	ANSI Grade	Scratch resistance	Tape resistance
Armor AXR 600	4 "/s	+	A	++	o
Armor AXR 800	4 "/s	+	B	++	o
Ricoh B120 E	4 "/s	++	A	+	+

ANSI (American National Standards Institute) Grade: information about barcode quality

A: excellent B: good C: acceptable D: readable with difficulty

++: excellent +: good o: acceptable -: poor

Chemical Resistance

The printed samples were wetted on the surface with a soft clean cotton cloth soaked in the test solution by wiping 10 times back and forth with light pressure. After 5 seconds they were dried with a clean dry soft cloth. After 15 minutes the evaluation took place.

	AXR7+	AXR8	R300	R510	SP330	B324	B110 CR	Z-4800	Z-5095	AXR 600	AXR 800	B120 E
Ad Blue	+	+	+	+	+	+	+	+	+	+	+	+
Anti-Freeze	+	+	+	+	+	+	+	+	+	+	+	+
Biodiesel	+	o	+	+	+	+	+	+	+	-	o	-
Bioethanol E85	-	+	+	+	+	+	+	-	+	-	o	-
Brake fluid	-	+	+	+	o	+	+	-	o	-	o	-
Cleaner solvent	+	+	+	+	+	+	+	+	+	-	-	-
Engine oil	+	+	+	+	+	+	+	+	+	+	+	o
Gasoline	-	o	-	+	-	-	-	-	-	-	-	-
Hard wax polish	+	+	+	+	+	+	+	+	+	-	-	-
Isopropanol	+	+	+	+	+	+	+	+	+	-	o	-
Spirit	-	+	+	+	+	+	+	-	+	-	o	-

+: good (no change) o: acceptable (minor change, still readable) -: poor

Chemicals:

Ad Blue: Aral, Anti-Freeze: Speedfrost "Speedfroil" 1:1 in water, Bioethanol E85: CropEnergies CropPower85
Brake Fluid: DOT 4 Synthetic (One Way), Cleaner Solvent: "Caramba" Cold Cleaner, Engine Oil: TOTAL quartz 700, 10 W 40
Gasoline: TOTAL Euro 95, Hard Wax Polish: „Nigrin" Hard Wax Polish

Appendix

Compliance Data

UL – Underwriters Laboratories (UL 969, Category PGJI2)

File Number: MH27538, Category PGJI2

This material is UL recognized for indoor use where exposed to high humidity or occasional exposure to water.

Application Surface	Max Temp (°C)	Min Temp (°C)
Alkyd paint	150	-40
Aluminum	150	-40
Galvanized steel	150	-40
Glass	150	-40
Stainless steel	150	-40
Nylon - Polyamide	100	-40
Polycarbonate	100	-40
Polyethylene terephthalate	100	-40
Acrylonitrile butadiene styrene	80	-40
Polyvinyl fluoride	80	-23

The UL certification includes the printing with EFI Jetrion, Jetrion 4000 and the following thermal transfer ribbons:

Armor	AXR 600, AXR 7+, AXR 8, AXR 800
Astro-Nova	R-5, RAF (Blue), RF, RY
Cembre	MG2-EPTR 991611, TPPS-060 842212
Coding Products	5440 (Red), 5640 (Blue), 5940
Dainippon	R300, R510, R510 (Blue), R510 (Green), R510 (Red), Signature Series (TM) Resin, TR4070, TR6070, TR6075
Dasco	DR 74, DR 84
Datamax	PGR, SDR, SDR Millennium, SDR-4, SDR-5, SDR-6, SDR-7, SDR-A, SDR-D
ITW	B324, M 95, R90, R91
limak	Primemark, Primemark 255, SH-36, SP-330, SP-410, SP-575
Intermec Corp.	053258-2, 054048-4, TMX1500, TMX3200
Italgrafica	TF330, TF335P
Japan Pulp and Paper	Resin 1, Resin 2 (Blue), Resin 2 (Green), Resin 2 (Red)
Japan Pulp and Paper GmbH	Sigma P
Kurz	K300, K500, K501
Mid-City Columbia Inc.	CGL 80HE, MCC-23HE
Monarch	9446
NCR	K3, Matrix Resin, PaceSetter, Perma Max, Promark III, Ultra V
Peak	Ultra Extreme, Ultra Premium
Pelikan	T064
RSI ID Technologies	Pressiza H, Pressiza K, Pressiza R, Pressiza S, Pressiza X
Ricoh	120 EC, B110C, B110CR (Suitable for outdoor use), B110CX, B120EC
Sato Corp.	Premier 1
Sony Chemicals	4072, 4075, 4080, 4085, 4571, 5070, TRX-75
Union Chemicar America	US300
United Barcode Industries	HR06
Zebra Technologies	5095, 5100, 5175, 5463, 5555, Z-1400, Z-3100, Z-4100

Appendix

Compliance Data

CSA – Canadian Standards Association

UL has tested this product according to the requirements described in CSA C22.2 No. 0.15.

This product is C-UL recognized for indoor use.

The details are listed in the UL file number MH27538, Category PGJ18.

Group	Application Surface	Max. Temperature (°C)
Metals	Bare, plated or enamelled steel; bare, anodized or enamelled aluminium	+150
Plastic Group III	Polycarbonate, acetates, acrylics	+80
Plastic Group IV	Polyethylene, polypropylene, polybutylene	+60
Plastic Group V	Polyamide, polyimide	+80
Plastic Group VI	ABS, styrene, styrene acrylonitrile	+80

The C-UL certification includes the printing with the following thermal transfer ribbons:

Armor	AXR 600, AXR 7+, AXR 8, AXR 800
Astro-Nova	RAF (Blue), RY
Cembre	MG2-EPTR 991611, TPPS-060 842212
Coding Products	5440 (Red), 5640 (Blue)
Dainippon	R300, R510, R510 (Blue), R510 (Green), R510 (Red), Signature Series (TM) Resin, TR4070, TR6070, TR6075
Datamax	SDR, SDR Millennium, SDR-5, SDR-6, SDR-7, SDR-A, SDR-D
ITW	B324, R90
limak	SP-575
Intermec Corp.	053258-2, 054048-4
Italgrafica	TF330, TF335P
Japan Pulp and Paper	Resin 1
Kurz	K500
Mid-City Columbia Inc.	CGL 80HE, MCC-23HE
NCR	Matrix Resin, Promark III
Peak	Ultra Extreme, Ultra Premium
RSI ID Technologies	Pressiza K, Pressiza S, Pressiza X
Ricoh	B110C, B110CR
Sato Corp.	Premier 1
Sony Chemicals	5070, TRX-75
Union Chemicar America	US300
Zebra Technologies	5100

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.