

### Facestock

A white polyethylene film with a print-receptive topcoat.

Basis Weight	78 g/m <sup>2</sup>	ISO 536
Caliper	79 µm	ISO 534
Density	0.988 g/cm <sup>3</sup>	ASTM D792

### Adhesive

A special permanent, acrylic based adhesive, for the pharmaceutical industry.

### Liner

BG42 white, a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	62 g/m <sup>2</sup>	ISO 536
Caliper	55 µm	ISO 534
Transparency	50 %	DIN 53147

### Laminate

Total Caliper	155 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	11 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-60 °C to 80 °C	
Peak Adhesive Stability (1hr)	150 °C	

### Adhesive Performance

A clear adhesive dedicated for the pharmaceutical and healthcare sector with lowest risk for migration, excellent UV resistance, good adhesion on polar and apolar surfaces. Adhesive for applications on small cylindrical containers, curved surfaces and suitable for use in labels to applied on high speed production lines. Can be sterilised in autoclave, gamma and ETO.

### Applications and Use


Applications are predominantly in home and personal care. Due to its flexibility the product is especially suitable for squeezable bottles and other flexible containers.

Typical applications include labels for use in the pharmaceutical industry, applications on small cylindrical containers, curved substrates and on other known substrates in the pharmaceutical industry. Due to the low risk of migration this adhesive is suitable for labelling plastic containers with liquid medicines eg. eye drops.

## AD853

### Fasson ®

#### PE85 TOP WHITE S692NP-BG42WH FSC



PE85 TOP WHITE

S692NP

BG42WH FSC



The mark of  
responsible forestry

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Conversion and Printing

The topcoated film can be printed by conventional and digital printing techniques such as UV flexo, UV Inkjet, screen, offset, letterpress, gravure, letterpress and hot or cold foiling processes. The topcoat is designed for optimal ink adhesion with UV-cured inks, including low migration inks, and is compatible with LED curing systems. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. On-press corona treatment is not advised. When applying a heavy ink load, the PE film may become brittle. Contact your ink supplier for advice on suitable, more flexible inks.

### Compliance and Approvals

The adhesive S692NP is suitable for contact with dry, moist and non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

The most recent cytotoxicity testing results obtained for S692NP, concluded no relevant genotoxicity effect was observed; clearing the required ISO 10993-5 status.

S692NP has a Drug Master File (DMF) submitted to the FDA. Letter of authorization can be issued on request.

This adhesive is covered by the Avery Dennison pharma change management programme. Please contact our technical representative to receive more information about our compliance statements and additional services.

### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2026 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.