

Facestock

A white, cast coated, high gloss finished, woodfree printing paper.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	80 g/m²	ISO 536
Caliper	85 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	72 g/m²	ISO 536
Caliper	63 µm	ISO 534

Laminate

Total Caliper	163 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	16 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 80 °C	

Adhesive Performance

The adhesive features high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates. Specially designed for wine labelling applications it allows easy conversion of difficult label shapes.

Applications and Use

The product is suitable for primary labelling of high and luxury goods with a traditional image, eg : wines, spirits and specialist foods.

Conversion and Printing

Cast coated paper is especially suitable for best quality letterpress, offset print and small font text printing due to its smooth surface. Due to the closed surface of these products inks should be carefully validated for these products.

Compliance and Approvals

The adhesive S2030 is suitable for contact with dry, moist, and fatty foodstuffs that have a reduction factor of 4 or higher in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

The laminate is made with FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)


Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AE959

Fasson ®

HIGH GLOSS WHITE FSC S2030-BG45WH FSC



HGWHITE FSC

S2030

BG45WH FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.