

## Facestock

A supercalandered yellow glassine paper, siliconized and with very low release.

Basis Weight	56 g/m²	ISO 536
Caliper	50 µm	ISO 534
Elongation MD	2 %	ISO 1924
Tensile MD	5,7 kN/m	ISO 1924
Tear str. MD	>200 mN	ISO 1974
Tear str. CD	>220 mN	ISO 1974
Release FTM10	15±10 cN/20m	Tested with
	m	TESA K7476

### Applications and Use

For direct and indirect adhesive coating applications. Particularly suitable as a release paper for die-cutting self adhesive labels.

## **Conversion and Printing**


Specially designed for high speed conversion, punching and perforation. Not suitable for printing due to silicone residues. Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.



Fasson ®

# LINER BG40BR LR FSC



## LINER BG40BR LR FSC



The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.