

#### **Facestock**

A matt/gloss, white, plain Polypropylene (PP) film with a print receptive layer on both sides. Ideal for IML label applications requiring high quality printing on the gloss side and good polymer adherance on the matt side.

| Basis Weight     | 55 g/m²                 | ISO 536      |
|------------------|-------------------------|--------------|
| Caliper          | 57 μm                   | ISO 534      |
| Elongation CD    | > 25 %                  | DIN 53455    |
| Elongation MD    | > 180 %                 | DIN 53455    |
| Gloss gloss side | 70 %                    | at 20° angle |
| Gloss matt side  | 7 %                     | at 60° angle |
| Whiteness        | 90 %                    | Berger       |
| Tensile Str. MD  | > 80 N/mm <sup>2</sup>  | OPMA         |
| Tensile Str. CD  | > 200 N/mm <sup>2</sup> | OPMA         |
| Shrinkage MD     | < 8 %                   | at 130°C and |
|                  |                         | 5'           |
| Shrinkage CD     | < 4 %                   | at 130°C and |
| Seal Temp. range | 120-140 °C              | 5'           |

# Surface Tension Level Applications and Use

This product is ideal for applications such as inmold labels for PP injection process, promotional banderoles around rigid packagings and wrap around labels on PET bottles.

> 36 mN/m

DIN 53364

### Conversion and Printing

The product can be converted by all conventional roll conversion technologies including: Letterpress, Offset, Screenprinting, UV flexo and Water-based flexo.


## Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

## **AG480**

## Fasson ®

## PP MATT WHITE 2S-60



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

## Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <a href="http://terms.europe.averydennison.com">http://terms.europe.averydennison.com</a>



©2023 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.