

Facestock

A clear Polyester film, siliconized and with low release.

Basis Weight	51 g/m ²	ISO 536
Caliper	36 µm	ISO 534
Elongation CD	80 %	DIN 53455
Elongation MD	95 %	DIN 53455
Tensile Str. MD	110 N/15mm	DIN 53455
Tensile Str. CD	140 N/15mm	DIN 53455
Release level	10 g/cm	FTM4 Tesa 7475

Applications and Use

For direct and indirect adhesive coating applications. The product typically is being used as a release liner for die-cutting special self-adhesive constructions on conversion presses, where a liner with high clarity, consistent thickness, very good dimensional stability and a high smoothness level is needed. It also has a good adhesive wet-out, resulting in high adhesive clarity.

Conversion and Printing

Specially designed for high speed conversion, punching and perforation.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AG515

Fasson®

LINER PET36 LR 1S



LINER PET36 LR 1S

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.