

Facestock

A white bi-axially oriented, polypropylene film with a print-receptive topcoat.

Basis Weight 50 g/m 2 ISO 536 Caliper 57 μm ISO 534

Adhesive

A special purpose removable, acrylic based adhesive.

Liner

BG40WH FSC, a supercalandered siliconized white glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight 57 g/m^2 ISO 536 Caliper $51 \mu \text{m}$ ISO 534

Laminate

Total Caliper 125 µm±10% ISO 534

Performance Data

Initial Tack 5.5 N/25mm FTM 9 Glass Peel Adhesion 90° 2.5 N/25mm FTM 2 St.St.

Min. Application Temp. 5 °C

Service Temperature -20 °C to 80 °C

Adhesive Performance

UVR145 is a removable acrylic based adhesive with excellent clarity and UV resistance. On a few substrates (e.g. PVC, Polystyrene, PC, ABS) the adhesion tends to become higher in the course of time and this may adversely affect functional removability. Due to the structure of the adhesive, when used with glassine liners, the liner may tend to curl. Preliminary testing is strongly recommended.

Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film, care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired


Conversion and Printing

The topcoated film can be printed by conventional and digital printing techniques such as UV flexo, UV Inkjet, screen, offset, letterpress, gravure, letterpress and hot or cold foiling processes. The topcoat is designed for optimal ink adhesion with UV-cured inks, including low migration inks, and is compatible with LED curing systems. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. On-press corona treatment is not advised. The material has very good register properties especially when a high number of different colors are used.

AG748

Fasson ®

PP60 TOP WHITE UVR145-BG40WH FSC



PP60 TOP WHITE	
----------------	--

	200
UVR145	33.2





The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



Compliance and Approvals

The adhesive UVR145 may be suitable for indirect food contact for the labeling of food packaging, assuming the end-user ensures the packaging serves as a functional barrier. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.