

### Facestock

A top coated bright silver, vacuum metallised printing paper.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	83 g/m <sup>2</sup>	ISO 536
Caliper	67 µm	ISO 534

### Adhesive

A general purpose permanent, acrylic based adhesive.

### Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	72 g/m <sup>2</sup>	ISO 536
Caliper	63 µm	ISO 534

### Laminate

Total Caliper	143 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	16 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 80 °C	

### Adhesive Performance

The adhesive features high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates. Specially designed for wine labelling applications it allows easy conversion of difficult label shapes.

### Applications and Use

Applications include labelling of quality products such as cosmetics, toiletries, luxury articles, prepacked food, wine, spirits, dairy products, stickers and promotional labelling.

### Conversion and Printing

Material has a print receptive topcoating in order to give good wettability and ink adhesion with suitable inks, may be printed using letterpress, screen, flexo, offset and gravure processes. Inks suitable for non absorbign surfaces should be used. Protection of the printed surface with a suitable varnish or overlamine is recommended for optimal scratch resistance. Metallised papers are sensitive to humidity and should not be exposed to extreme heat, cold or humidity as this may affect the printing performance and surface appearance.

### Compliance and Approvals

The adhesive S2030 is suitable for contact with dry, moist, and fatty foodstuffs that have a reduction factor of 4 or higher in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

The laminate is made with FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

## AH966

## Fasson ®

### MP PLUS SILVER FSC S2030-BG45WH FSC



MP PLUS SILVER FSC

S2030

BG45WH FSC



*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.