

Facestock

A white bi-axially oriented, polypropylene film with a print-receptive topcoat.

Basis Weight	49 g/m ²	ISO 536
Caliper	57 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG40WH FSC, a supercalandered siliconized white glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	57 g/m ²	ISO 536
Caliper	51 µm	ISO 534

Laminate

Total Caliper	123 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	10 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 80 °C	

Adhesive Performance

S692N is a clear permanent adhesive featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates.

S692N in combination with polyolefin face materials (PE85, PP, Global MDO) is approved by Recyclclass as fully compatible with the rigid HDPE recycling stream.

Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film, care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired

Conversion and Printing

The topcoated film can be printed by conventional and digital printing techniques such as UV flexo, UV Inkjet, screen, offset, letterpress, gravure, letterpress and hot or cold foiling processes. The topcoat is designed for optimal ink adhesion with UV-cured inks, including low migration inks, and is compatible with LED curing systems. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. On-press corona treatment is not advised. The material has very good register properties especially when a high number of different colors are used.

Compliance and Approvals


The adhesive S692N is suitable for contact with dry, moist and fatty foodstuffs with a reduction factor of 3 or higher in this construction.

For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

AL597

Fasson®

PP60 TOP WHITE S692N-BG40WH FSC



PP60 TOP WHITE

S692N

BG40WH FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2026 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.