

Facestock

A matt, transparent, selfwound biaxial oriented Polypropylene (BOPP) film coated with a clear emulsion acrylic adhesive on one side. Ideal for PSL overlamination applications requiring easy apply on press and low glare surface. Below "Caliper" value refers to total product thickness including the adhesive.

Basis Weight	36 g/m ²	ISO 536
Caliper	38 µm	ISO 534
Application temperatur range	0 to +65 °C	
Caliper (film only)	25.4 µm	T411
Haze	64 %	ASTM D1003
Operating temperatur range	-20 to +90 °C	
Peel adhesion to steel	368 gr/in	180°; 30 min; 12 in/min T494
Tensile str. TAPPI MD	20 lbs/in	T494
Elongation TAPPI MD	190 %	T494
Elongation TAPPI CD	70 %	T494
Peel adhesion to steel 24H	453 gr/in	180°; 24H; 12 in/min

Applications and Use

The use of overlaminating film can aid in label dispensing. Commonly used to enhance durability in harsh environments. Appropriate for high moisture and high abrasion packaging applications, such as durable goods labeling. Can also be used for reinforcing printed media or applied as an overlaminate for flexible packaging applications. This overlam film offers a low glare surface.

Conversion and Printing

This film is not designed for printing. When diecutting overlaminated pressure sensitive constructions, dies should be clean, sharp, and tooled for this purpose. **IMPORTANT NOTE - Fish eyes** In some cases, during the slitting process, air can be trapped under the self-wound film – referred to as 'fish eyes' or hazy adhesive spots. This is a common problem, and these spots will usually disappear within a day as the adhesive continues to flow out onto the substrate. Some inks may need further attention or testing. Haziness after overlamination can also arise from insufficiently high application pressures or with some particularly demanding substrates.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AN321

Fasson ®

SELFWOUND PP 25 CL MT



SELFWOUND PP 25 CL MT

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.