

Facestock

A bi-axially oriented, gloss clear polypropylene film with a print-receptive topcoating

Basis Weight	47 g/m ²	ISO 536
Caliper	50 µm	ISO 534

Adhesive

An extra permanent, acrylic based adhesive.

Liner

A clear polyester liner giving optimum smoothness to the adhesive layer.

Basis Weight	42 g/m ²	ISO 536
Caliper	30 µm	ISO 534

Laminate

Total Caliper	103 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	19 N/25mm	FTM 9 Glass
Peel Adhesion 90°	11 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-40 °C to 90 °C	

Adhesive Performance

S700 is a reinforced permanent acrylic based adhesive with very good initial tack and adhesion to a wide range of substrates.

Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film, care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired. For optimal dispensing a relatively high tension on the backing and a sharp beak are recommended.

Conversion and Printing

The top coated face material can be printed by letterpress, flexo, gravure and screen, giving good printing results with solvent, UV curing, waterbased inks and hot-foil blocking. Especially with waterbased and UV screen inks, careful selection of the ink and preliminary testing is essential. Material shows excellent register stability on press and excellent flat bed conversion while rotary and magnetic dies need additional care.

Press stability is good with stable, consistent register during conversion. Flat bed performance is good while solid and magnetic rotary dies need additional care. (Die bearers must be adjusted to the polyester liner).


Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AN873

Fasson ®

PP NG TOP CLEAR S700-PET30



PP NG TOP CLEAR

S700

PET30

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.
If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com*

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.