

Facestock

A low-weight, white, microporous spun-bonded Polyolefin film with a calendered surface on both sides. Ideal for tag applications requiring enhanced smoothness for improved TT printing and high tear resistance.

Basis Weight	76 g/m ²	ISO 536
Caliper	170 µm	ISO 534
Burst Strength	1180 kPA	ISO 2758
Delamination MD	>1.15 N	ASTM D2724-87
Opacity	91 %	ISO 2471
Tensile MD	200 N	ISO 1924
Tensile CD	215 N	ISO 1924
Tear Elmendorf MD	>3 N	DIN EN 21974
Tear Elmendorf CD	>3 N	DIN EN 21974

Applications and Use

This product is ideal for applications such as self-tie luggage and tree tags, sew-in or stapled labels and heavy postal bag tags.

Conversion and Printing

The product can be converted by all conventional roll conversion technologies including: Letterpress, Offset, Screenprinting, UV flexo and Water-based flexo.

This product is also suitable for variable information printing in: Thermal Transfer printing systems providing high quality barcode images. The print quality depends on the correct match of the ribbon, printer and substrate.

Very good test results on the following digital printing presses: HP Indigo.

Thermal transfer printing can be recommended with this facestock. For best scratch resistance resin or wax/resin ribbons are recommended. Printing tests need to be performed with the specific printer and TT ribbon to evaluate the printing results and performance.

IMPORTANT NOTES: Avoid the use of large quantities of volatile solvents with the letterpress and offset processes.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

AO323

Fasson®

TYVEK BRILLION 4173D



TYVEK BRILLION 4173D

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.