

Facestock

A white polyester-faced laminated pouching material used in packaging of snack foods. Adhesive coated two layer laminate (PET 12 μ SiOx/PE white 50 μ).

Basis Weight	72.6 g/m ²	ISO 536
Caliper	62 μ m	ISO 534
Elongation at break CD	>60 %	DIN 53455
Elongation at break MD	>60 %	DIN 53455
Oxygen Permeability (23°C; 50%RH)	0,4 - 0,6 cm ³ /m ² /24 hr	ASTM D3985
2% Secant Modulus MD	>850 N/mm ²	DIN EN ISO 527 T 3
2% Secant Modulus MD	>900 N/mm ²	DIN EN ISO 527 T 3
Flexural Modulus Fmax MD	>250 mN	SCAN P
Flexural Modulus Fmax CD	>300 mN	29/DIN 52 121
Tear Elmendorf MD	>0.25 N	SCAN P
Tear Elmendorf CD	>0.35 N	29/DIN 52 121
Tensile Stren. MD	>50 N/mm ²	DIN EN 21974
Tensile Stren. CD	>45 N/mm ²	DIN EN 21974
Water Vapor Transmission Rate (38°C; 90% RH)	0,1 - 0,2 g/m ² /24 hr	ISO 527-3
Sealing Strength	>30 N/15mm	ISO 527-3
		529@140°C/5 bar/0.5sec
Coefficient of Friction Inside/Inside	0,15 - 0,30 μ s	ASTM D1895
Coefficient of Friction Outside/Outside	0,30 - 0,50 μ s	ASTM D1895

Applications and Use

Heatsealable Flexible packaging laminates for nuts and other oxygen sensitive salted snacks or general-purpose snack good applications. White PET with Nano coating providing reduced OTR.

Conversion and Printing

The white corona treated PET face provides printability via Flexo.

Shelf Life

To obtain optimal performance, use this product within half a year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AO602

Fasson ®

SNACK WEB WHITE62 NANO



SNACK WEB WHITE62 NANO

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2023 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.