

Facestock

A white woodfree, thermal coated paper, with a top and backside protective coating. The black imaging thermosensitive coating provides very good resistance to moisture, fat, oil, alcohol, etc. This product is produced without the use of phenols (Phenols free).

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	75 g/m ²	ISO 536
Caliper	74 µm	ISO 534
Brightness	>87 %	ISO 2470
CIE-whiteness	>105 %	ISO 11475
Opacity	>86 %	ISO 2471
Tensile MD	>4.7 kN/m	ISO 1924
Tensile CD	>2.3 kN/m	ISO 1924
Tear Strength MD	>325 mN	ISO 1974
Tear Strength CD	>370 mN	ISO 1974
Surface smoothness; Bekk	>1000 s	ISO 5627

Adhesive

A general purpose removable, rubber based adhesive.

Liner

BG40 brown, supercalendered glassine paper.

Basis Weight	53 g/m ²	ISO 536
Caliper	46 µm	ISO 534

Laminate

Total Caliper	136 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	2 N/25mm	FTM 9 Glass
Peel Adhesion 90°	1 N/25mm	FTM 2 St.St.
Min. Application Temp.	-20 °C	
Service Temperature	-40 °C to 80 °C	

Adhesive Performance

The adhesive is suitable for general application on a wide range of substrates, featuring good initial tack and adhesion combined with excellent removability. In addition the adhesive has superb low temperature performance. **Remark:** Application to porous substrates such as paper and board, or prolonged exposure to UV light may adversely affect clean removability. Removable adhesive, by nature, have a low cohesion and might be subject to variation in the product aesthetics which could be observed on the web rolls as long as the material is not used. We recommend to store the material with the inner core in vertical position after delivery.

Applications and Use

This product is ideal for applications such as parking tickets, transportation tickets and receipts.


Heat Resistance - At 90°C the black density of the background image will increase.

- > Test method: exposure @ 80°C for 1hr
- > Image Density: >1.20 odu

AO639

Fasson ®

THERMAL TOP S8 PF FSC R100 DEC-BG40BR



THERMAL TOP S8 PF FSC

R100

BG40BR



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

- > Background Density: <0.20 odu
- > Test method: exposure @ 90°C for 1hr
 - > Image Density: >1.20 odu
 - > Background Density: <0.25 odu

R100 removes clean from many substrates from polymeric (PET, PP, ABS, PS), greeting cards, aluminium, stainless steel and glass (not suitable for window labelling)

Conversion and Printing

The product can be converted by all conventional roll conversion technologies including: Letterpress, Offset, Screenprinting, UV flexo and Water-based flexo. This product is also suitable for variable information printing in: Direct thermal printing systems at printing speeds up to 200 mm/sec (based on the printer's set up).

IMPORTANT NOTES: Due to the thermographic properties, exposure above 50°C may cause premature imaging or discolouration. Inks containing alcohol or volatile organic solvents may cause discolouration of the thermosensitive coating. It is advisable to test inks and varnishes before conversion.

Compliance and Approvals

The adhesive R100 is suitable for contact with dry, moist, and non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.