

Facestock

A heatsealable, white, semi-gloss coated paper faced laminate used in flexible packaging of dry goods. Extrusion coated three layer laminate: C1S paper 50gsm / LDPE 12 / 6,5μ Alu foil / 23g Coex Surlyn.

Basis Weight	103 g/m ²	ISO 536
Caliper	83 μm	ISO 534
Burst Strength	>160 KPa	ASTM D774
Elongation CD	>6.0 %	ASTM D828
Elongation MD	>1.5 %	ASTM D828
Heat Seal front	140-160 °C	
Moisture vapor transmission rate	<0.5 g/sqm/24 h	Astm F 1249 (38°C; 90%RH)
Oxygen Permeability (23°C; 50%RH)	<0.5 cm ³ /m ² /24 hr	ASTM D3985
Tensile strength MD	> 5.8 daN/15 mm	ASTM D828
Tensile strength CD	> 3.8 daN/15 mm	ASTM D828
Tear Strength MD	>500 mN	ISO 1974
Tear Strength CD	>500 mN	ISO 1974

Applications and Use

Paper-faced laminated pouching material used in flexible packaging of dry goods such as instant coffee, seeds, dehydrated sauces and soups. Very good sealing properties due to the thick layer of Coex Surlyn.

Conversion and Printing

This high quality coated paper is suitable for printing in flexo, gravure and letterpress. Statement of Practical Use: This product should be tested thoroughly under end-user conditions to ensure it meets the requirements of the specific application. This is particularly the case if the intended use is for food. Avery Dennison therefore request the client to do sufficient testing to make sure that the intended application does not cause any harm and is safe.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AO646

Fasson ®

PAPER WEB50 SURLYN



PAPER WEB50 SURLYN

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2023 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.