

Facestock

A polyethylene film with a print-receptive top-coat.

Basis Weight	84 g/m ²	ISO 536
Caliper	82 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

Liner rBG40 BROWN, a siliconized supercalendered glassine paper with 15% recycled (PCR) content. Being produced with recycled material, there is a possible higher incidence of impurities, visible fibers, and slight variation in tone.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	54 g/m ²	ISO 536
Caliper	47 µm	ISO 534

Laminate

Total Caliper	147 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	10 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 80 °C	

Adhesive Performance

S692N is a clear permanent adhesive featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates.

S692N in combination with polyolefin face materials (PE85, PP, Global MDO) is approved by Recyclclass as fully compatible with the rigid HDPE recycling stream.

Applications and Use

Flexible labels for application to squeezable bottles, plastic bags and other containers. Also recommended for applications where PVC labels are undesirable for environmental reasons.

Special care should be given during dispensing around the gum free area.

Conversion and Printing

The modified acrylic-based top-coating allows printing by all the conventional print technologies including UV-letterpress, screen and water-based flexo. Corona treatment is not required.

The special product lay-out could have an influence on conversion speed.

Compliance and Approvals


The adhesive S692N is suitable for contact with dry, moist and fatty foodstuffs with a reduction factor of 3 or higher in this construction.

For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

AS338

Fasson ®

PE TOP MATT WHITE S692N SGP-rBG40BR FSC



PE TOP MATT WHITE

S692N

rBG40BR FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.