

### Facestock

A matt white, high density polyethylene film with a specific inkjet receptive coating for dye water based inks and good water resistance.

Basis Weight	72 g/m <sup>2</sup>	ISO 536
Caliper	105 µm	ISO 534

### Adhesive

A general purpose permanent, rubber based adhesive.

### Liner

Liner rBG40 BROWN, a siliconized supercalendered glassine paper with 15% recycled (PCR) content. Being produced with recycled material, there is a possible higher incidence of impurities, visible fibers, and slight variation in tone.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	53 g/m <sup>2</sup>	ISO 536
Caliper	46 µm	ISO 534

### Laminate

Total Caliper	170 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	18 N/25mm	FTM 9 Glass
Peel Adhesion 90°	9 N/25mm	FTM 2 St.St.
Min. Application Temp.	0 °C	
Service Temperature	-40 °C to 70 °C	

### Adhesive Performance

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates. Particularly good performance at lower temperatures, e.g. labeling of chilled products.

### Applications and Use

The product is specially designed for use in inkjet printers however due to the large variation of printers and inks we strongly recommend preliminary printingtest to optimize the printing quality.

### Conversion and Printing

The absorbent top coating provides a 'paper like' surface for conventional preprinting. Material shows very good register stability on pressand flat bed conversion while rotary and magnetic dies need additional care. Due to the extensible nature of the face, care shouldbe taken with die specification; sharp dies are essential.

### Compliance and Approvals


The adhesive S2045N is suitable for contact with dry and moist, non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

Adhesive S2045N has attained the two star certification for biobased content according to EN 16640, meaning that S2045N contains certified Biobased Carbon Content of at least 40%. (TÜV AUSTRIA licensee number: S0259)

## AU494

## Fasson®

### WBIJ PEHD MATT WHITE S2045N-rBG40BR FSC



WBIJ PEHD MATT WHITE

S2045N

rBG40BR FSC



The mark of  
responsible forestry

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*



\*The OK biobased certification is only applicable to the adhesive S2045N.

### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2026 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.