

Facestock

A bi-axially oriented, gloss white polypropylene film with a print-receptive top-coat.

Basis Weight	90 g/m ²	ISO 536
Caliper	92 µm	ISO 534

Adhesive

A special permanent, acrylic based adhesive, for the pharmaceutical industry.

Liner

BG40WH FSC, a supercalandered siliconized white glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	57 g/m ²	ISO 536
Caliper	51 µm	ISO 534

Laminate

Total Caliper	162 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	11 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-60 °C to 80 °C	
Peak Adhesive Stability (1hr)	150 °C	

Adhesive Performance

A clear adhesive dedicated for the pharmaceutical and healthcare sector with lowest risk for migration, excellent UV resistance, good adhesion on polar and apolar surfaces. Adhesive for applications on small cylindrical containers, curved surfaces and suitable for use in labels to applied on high speed production lines. Can be sterilised in autoclave, gamma and ETO.

Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired.

Typical applications include labels for use in the pharmaceutical industry, applications on small cylindrical containers, curved substrates and on other known substrates in the pharmaceutical industry. Due to the low risk of migration this adhesive is suitable for labelling plastic containers with liquid medicines eg. eye drops.


Conversion and Printing

The modified acrylic based topcoating allows printing by the usual printing technologies including letterpress, flexo, gravure and screen printing, giving good results with solvent, UV curing and water based inks. Good acceptance of hot foil blocking. Conversion with flatbed and solid/magnetic rotary dies is very good. Square corners should be avoided.

AY009

Fasson ®

PP90 TOP WHITE
S692NP-BG40WH FSC



PP90 TOP WHITE

S692NP

BG40WH FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Compliance and Approvals

The adhesive S692NP is suitable for contact with dry, moist and non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

The most recent cytotoxicity testing results obtained for S692NP, concluded no relevant genotoxicity effect was observed; clearing the required ISO 10993-5 status.

S692NP has a Drug Master File (DMF) submitted to the FDA. Letter of authorization can be issued on request.

This adhesive is covered by the Avery Dennison pharma change management programme. Please contact our technical representative to receive more information about our compliance statements and additional services.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.