

### Facestock

A clear polyester film which has been slip treated on one side to give better converting speeds.

Basis Weight	105 g/m <sup>2</sup>	ISO 536
Caliper	75 µm	ISO 534
Elongation at break CD	85 %	ASTM D 882-83
Elongation at break MD	155 %	ASTM D 882-83
Haze	<1.0 %	ASTM D1003
Shrinkage MD	1.0 %	DIN 40634 (150°; 15 min)
Shrinkage CD	0.7 %	DIN 40634 (150°; 15 min)
Tensile strength MD	19.0 Kg/mm <sup>2</sup>	ASTM D 882-83
Tensile strength CD	28.0 Kg/mm <sup>2</sup>	ASTM D 882-83
Upper Melt Temperature	255 °C	ASTM E794-85

### Applications and Use

This clear film presents good handling qualities. The film is suitable for applications where very high transparency is important. This product is mainly used in "rigid box with window" type of packaging applications where there is a need to display the inside of the packaging.

### Conversion and Printing

This film is not intended to take additional print.


### Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

## AY100

## Fasson ®

## PET CLEAR 1S-75



PET CLEAR 1S-75

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.