

Facestock

A white, two side satin matt coated solid bleached sulphate (SBS) board with outstanding bulk and stiffness.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

,		
Basis Weight	220 g/m ²	ISO 536
Caliper	230 µm	ISO 534
Brightness	94 %	ISO 2470
Gloss 75° angle	40 %	T480
Whiteness	127 %	ISO 11475
Tensile Str. MD	21.0 kN/m	ISO 1924
Tensile Str. CD	10.5 kN/m	ISO 1924
Tear str. MD	2050 mN	ISO 1974
Tear str. CD	2300 mN	ISO 1974
Stiffness Taber 15° MD	5.2 mNm	ISO 2493
Stiffness Taber 15° CD	2.4 mNm	ISO 2493
Roughness; PPS	1.2 μ	ISO 8791-4

Applications and Use

This card is suitable for garment price tags, door hangers and other tags requiring superior stiffness. Other typical applications include, folded boxes, brochures, covers for brochures and annual reports or corporate graphics such as folders, business cards and invitations.

Conversion and Printing

This product is suitable for printing by letterpress, flexo (UV and waterbased) offset and screen processes. Variable imprinting with thermal transfer are also suitable for this product. Finishing techniques include embossing, film and foil laminating, varnishing, die cutting, folding, scoring and cutting.


Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AY521

Fasson ®

MC ELITE CARD 2S-220 FSC



MC ELITE CARD 2S-220 FSC



responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.