

### Facestock

A low-weight, white, microporous spun-bonded Polyolefin film with a corona treatment on both sides. Ideal for medical and pharmaceutical packaging applications.

Basis Weight	74.7 g/m <sup>2</sup>	ISO 536
Caliper	199 µm	ISO 534
Burst Strength	1207 KPa	ISO 2758
Moisture vapor transmission rate	>1600 g/sqm/2	TAPPI T523
Porosity Bendtsen	540 ml/min	ISO 5636
Porosity Gurley	22 s/100cc	Tappi T460
Internal Bonding	2.6 N	ASTM D 2724
Opacity Color Touch	92 %	ISO 2471
Tear Elmendorf MD	3.2 N	ASTM D 1424
Tear Elmendorf CD	4.0 N	ASTM D 1424
Tensile MD	205 N	ISO 1924
Tensile CD	219 N	ISO 1924

### Applications and Use

This product is ideal for applications such as self-tie luggage and tree tags, sew-in or stapled labels and heavy postal bag tags.

### Conversion and Printing

The product can be converted by all conventional roll conversion technologies including: Letterpress, Offset, Screenprinting, UV flexo and Water-based flexo.

This product is also suitable for variable information printing in: Thermal Transfer printing systems. The print quality depends on the correct match of the ribbon, printer and substrate.

Very good test results on the following digital printing presses: HP Indigo.

### IMPORTANT NOTES:

- 1) Avoid the use of large quantities of volatile solvents with the letterpress and offset processes.
- 2) Although Tyvek® is printable on both sides, it is recommended to use the smooth side for one-sided or full-coverage printing, and for Thermal Transfer printing.

### Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

# AY586

## Fasson®

### TYVEK 1073B



TYVEK 1073B

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*



©2026 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.