

Facestock

A matt finished polyester film with backside metallisation. The smooth surface is covered with a topcoat for very good ink anchorage.

Basis Weight	72 g/m ²	ISO 536
Caliper	50 µm	ISO 534

Adhesive

S8039 is a clear rubber hybridised acrylic adhesive.

Liner

BG42Wh BSS: on both sides siliconized glassine paper, woodfree, super calandered and extremely tough and tear-resistant despite its thinness.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	64 g/m ²	ISO 536
Caliper	55 µm	ISO 534

Laminate

Total Caliper	135 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	21 N/25mm	FTM 9 glass
Min. Application Temp.	+5 °C	
Service Temperature	-40 °C to 150 °C	
Adhesive Coat Weight	30 g/m ²	FTM12
Adhesive Type	rubber hybridised acrylic	
Peel Adhesion 90° - 24hr	22 N/25mm	FTM 2 st.st. 24hr

Adhesive Performance

S8039 features extremely high final adhesion on a wide variety of surfaces including textured and low surface energy substrates. Excellent chemical resistance.

Applications and Use


This face-stock was specially developed for labels on Durables Goods, including automotive parts, electronic equipment and home appliances.


This is a premium product for the automotive industry using patented Avery Dennison RHA (rubber hybridised acrylic) adhesive technology. It is designed primarily for creating labels to be applied onto low surface energy plastic automotive parts or other rough or low surface energy surfaces. The increased coat weight of this adhesive (30 g/m²) aids labelling rough substrates. The product is briefly repositionable and then the adhesion increases to very high ultimate peelstrength. S8039 products are engineered to be resistant to - also harsh - chemicals commonly found in the automotive and electronics industry.

AZ209

Fasson®

TRANSF PET MATT CHR TOP S8039-BG42WH BSS FSC



TRANSFER PET MAT CHR TOP	
--------------------------	--

S8039	
-------	---

BG42WH BSS FSC	
----------------	---



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Because of the high coat weight and high tack of the adhesive, there is a risk of adhesive ooze. Special care has to be taken in the conversion process. It is recommended to contact the supplier of die cutting equipment to specify the most suitable tool. Good results have been achieved using a 60° cutting angle with laser hardening and a no-stick coating.

Conversion and Printing

Excellent results can be achieved with thermal transfer printers equipped with conventional or near-edge print heads using resin ribbons. This product is qualified by EFI Jetrion and Durst for UV inkjet printing. Transfer PET Mat Chr Top can also be printed by all conventional roll label techniques, including flexo, UV letterpress, silkscreen. For easy diecutting sharp corners should be avoided.

Compliance and Approvals

This product is UL and C-UL recognized (UL 969, CSA C22.2 No. 0.15). The UL file number is MH27538.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Appendix

UL and CSA recognition

This product meets the requirements as stated in UL 969 and CSA C22.2 No. 0.15 for indoor and outdoor use. The UL file number is MH27538. For specific information on approved conditions, see appendix.

Performance Data

Note: the following technical data should be considered representative or typical only and should not be used for specification purposes.

Peel Adhesion:

FTM1: 180°, 300 mm/min, dwell time: 48 hours

Surface	N/25mm
ABS	27,0
Aluminum	25,0
Automotive lacquered panels	28,0
Glass	28,5
HDPE	14,5
LDPE	13,5
Polycarbonate (PC)	27,5
Polyester (PET)	28,0
Polypropylene (PP)	26,0
Polystyrene (PS)	26,5

Due to the unique RHA technology we strongly recommend waiting for 24 hours after application before performing any adhesive testing.

Chemical Resistance:

The performance results are based on 4 hours immersions at room temperature unless otherwise noted. Samples were applied to the test panel and conditioned for 24 hours before immersion and evaluated immediately upon removal. Peel adhesion was measured according to FTM1.

Chemical	Test Substrate	N/25mm	Visual appearance	Edge Penetration
Ad Blue	Stainless Steel	21,0	No change	0 mm
Biodiesel	Stainless Steel	26,5	No change	0 mm
Bioethanol E85	Glass	24,5	No change	2 mm
Brake Fluid	Glass	29,0	No change	0 mm
Diesel	Glass	27,0	No change	0,5 mm
Engine Oil	Glass	25,5	No change	0 mm
Gasoline	Glass	22,0	No change	3,5 mm
Heptane	Glass	22,0	No change	4 mm
Water, distilled	Aluminum	15,0	No change	0 mm
Windshield washer	Stainless Steel	25,0	No change	0 mm

Chemicals: Ad Blue: Aral, Bioethanol E85: CropEnergies CropPower85, Brake Fluid: DOT 4 Synthetic (One Way) Diesel: TOTAL, Engine Oil: TOTAL quartz 700, 10 W 40, Gasoline: TOTAL Euro 95

Appendix

Thermal Transfer Printing:

Printability – Physical Resistance

Flat head printers (tests were performed with the printer Zebra XII 140):

Ribbon	Settings speed energy		Print Quality	ANSI Grade	Scratch resistance	Tape resistance
Armor AXR7+	3	20	++	D ¹	++	++
Armor AXR8	3	15	++	D ¹	++	++
DNP R300	3	15	++	D ¹	++	++
DNP R510	3	20	++	D ¹	++	++
limak SP330	3	15	++	D ¹	++	++
ITW B324	3	15	++	D ¹	++	++
Ricoh B110CR	3	15	++	D ¹	++	++

Near edge printers (tests were performed with the printer Avery TTX 450 – Near Edge):

Ribbon	Settings	Print Quality	ANSI Grade	Scratch resistance	Tape resistance
Armor AXR 600	4 "/s	++	D ¹	++	++
Armor AXR 800	4 "/s	+	D ¹	++	o
Ricoh B120 E	4 "/s	++	D ¹	+	+

ANSI (American National Standards Institute) Grade: information about barcode quality

A: excellent B: good C: acceptable D: readable with difficulty

++: excellent +: good o: acceptable -: poor

¹ The print quality is good, but due to the reflection of metallised films the contrast is low

Chemical Resistance

The printed samples were wetted on the surface with a soft clean cotton cloth soaked in the test solution by wiping 10 times back and forth with light pressure. After 5 seconds they were dried with a clean dry soft cloth. After 15 minutes the evaluation took place.

	AXR7+	AXR8	R300	R510	SP330	B324	B110 CR	AXR 600	AXR 800	B120 E
Ad Blue	+	+	+	+	+	+	+	+	+	+
Anti-Freeze	+	+	+	+	+	+	+	+	+	+
Biodiesel	+	o	+	+	+	+	+	-	o	-
Bioethanol E85	-	+	+	+	+	+	+	-	o	-
Brake fluid	-	+	+	+	o	+	+	-	o	-
Cleaner solvent	+	+	+	+	+	+	+	-	-	-
Engine oil	+	+	+	+	+	+	+	+	+	o
Gasoline	-	o	-	+	-	-	-	-	-	-
Hard wax polish	+	+	+	+	+	+	+	-	-	-
Isopropanol	+	+	+	+	+	+	+	-	o	-
Spirit	-	+	+	+	+	+	+	-	o	-

+: good (no change) o: acceptable (minor change, still readable) -: poor

Chemicals:

Ad Blue: Aral, Anti-Freeze: Speedfrost "Speedfroil" 1:1 in water, Bioethanol E85: CropEnergies CropPower85
Brake Fluid: DOT 4 Synthetic (One Way), Cleaner Solvent: "Caramba" Cold Cleaner, Engine Oil: TOTAL quartz 700, 10 W 40
Gasoline: TOTAL Euro 95, Hard Wax Polish: „Nigrin" Hard Wax Polish

Appendix

Compliance Data

UL – Underwriters Laboratories (UL 969, Category PGJ12)

File Number: MH27538, Category PGJ12

This material is UL recognized for indoor and outdoor use where exposed to high humidity or occasional exposure to water.

Application Surface	Max Temp (°C)	Min Temp (°C)
Acrylic powder paint	150	-40
Aluminum	150	-40
Chromate treated metal	150	-40
Epoxy powder paint	150	-40
Galvanized steel	150	-40
Polyester powder paint	150	-40
Polyurethane powder paint	150	-40
Stainless steel	150	-40
Alkyd paint	125	-40
Acrylic paint	100	-40
Epoxy paint	100	-40
Nylon - Polyamide	100	-40
Polyester paint	100	-40
Acrylonitrile butadiene styrene (ABS)	80	-40
Acrylonitrile styrene acrylate (ASA)	80	-40
Polyphenylene oxide/ether	80	-40
Polystyrene	80	-40
Polypropylene	80	-40
Polycarbonate	60	-40
Polyethylene	60	-23

The UL certification includes the printing with EFI Jettron, “Jettron 4000”, Durst “Tau 330 RSC”, Xeikon “PantherCure UV”, Domino “N610i” and the following thermal transfer ribbons:

Armor	AXR 600, AXR 7+, AXR 8
Astro-med	R-5, RAF, RF, RY
Coding Products	5440 (Red), 5640 (Blue), 5940
Dainippon	R300, R510, R510 (Blue), R510 (Green), R510 (Red, indoor use only), Signature Series (TM) Resin, TR4070, TR6070, TR6075
Dasco	DR 74, DR 84
Datamax	PGR, SDR, SDR Millennium, SDR-4, SDR-5, SDR-6, SDR-7, SDR-A, SDR-D
ITW	B324, M 95, R90, R91
limak	Primemark, Primemark 255, SH-36, SP-330, SP-410
Intermec Corp.	053258-2, 054048-4, TMX1500, TMX3200
Japan Pulp and Paper	Resin 1, Resin 2 (Blue, Green), Resin 2 (Red, indoor use only), Sigma P
Kurz	K300, K500, K501
Mid-City Columbia Inc.	CGL 80HE, MCC-23HE
Monarch	9446
NCR	K3, Matrix Resin, PaceSetter, Perma Max, Promark III, Ultra V
Peak	Ultra Extreme, Ultra Premium
RSI ID Technologies	Pressiza H, Pressiza K, Pressiza R, Pressiza S, Pressiza X
Ricoh	120 EC, B110C, B110CR, B110CX
Sato Corp.	Premier 1
Sony Chemicals	4072, 4075, 4080, 4085, 4571, 5070, TRX-75
Union Chemicar Am.	US300
United Barcode Industries	HR06
Zebra Technologies	5095, 5100, 5175, 5463, 5555, Z-1400, Z-3100, Z-4100

Appendix

Compliance Data

CSA – Canadian Standards Association

UL has tested this product according to the requirements described in CSA C22.2 No. 0.15.
This product is C-UL recognized for indoor and outdoor use.
The details are listed in the UL file number MH27538, Category PGJ18.

Group	Application Surface	Max. Temperature (°C)
Metals	Bare, plated or enameled steel; bare, anodized or enameled aluminium	150
Electrostatic coated metal A	Polyester powder coat paint	150
Electrostatic coated metal C	Epoxy powder coat paint	150
Electrostatic coated metal D	Polyurethane powder coat paint	150
Plastic Group II	Polyphenylene oxide, polyphenylene sulphide	80
Plastic Group III	Polycarbonate, acetates, acrylics	80
Plastic Group IV	Polyethylene, polypropylene, polybutylene	80
Plastic Group V	Polyamide, polyimide	80
Plastic Group VI	polystyrene, styrene acrylonitrile, ABS	80
Plastic Group VII	PVC (rigid), PVC plasticized	80
Plastic Group VIII	Glass-filled polyester, glass-filled epoxy	80

The C-UL certification includes the printing with EFI Jetrion, "Jetrion 4000", Durst "Tau 330 RSC", Xeikon "PantherCure UV", Domino "N610i" and the following thermal transfer ribbons:

Armor	AXR 600, AXR 7+, AXR 8
Astro-med	RAF, RF, RY
Coding Products	5440 (Red), 5640 (Blue)
Dainippon	R300, R510, R510 (Blue), R510 (Green), R510 (Red, indoor use only), Signature Series (TM) Resin, TR4070, TR6070, TR6075
Datamax	SDR, SDR Millennium, SDR-5, SDR-6, SDR-7, SDR-A, SDR-D
ITW	B324, R90
limak	SP-575
Intermec Corp.	053258-2, 054048-4
Japan Pulp and Paper	Resin 1
Kurz	K500
Mid-City Columbia Inc.	CGL 80HE, MCC-23HE
NCR	Matrix Resin, Promark III
Peak	Ultra Extreme, Ultra Premium
RSI ID Technologies	Pressiza K, Pressiza S, Pressiza X
Ricoh	B110C, B110CR
Sato Corp.	Premier 1
Sony Chemicals	5070, TRX-75
Union Chemicar Am.	US300
Zebra Technologies	5100, 5175

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.