

### **Facestock**

A white bi-axially oriented polypropylene film with a specific topcoating for very good transfer and anchorage of Electrolnk as used in the Indigo process, allowing a wide range of design and performance choices on rigid packaging and bottles.

Basis Weight  $56 \text{ g/m}^2$  ISO 536 Caliper  $57 \mu \text{m}$  ISO 534

#### Adhesive

A special purpose permanent, rubber based adhesive for deepfreeze and low temp

# Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight 69 g/m² ISO 536 Caliper 60 µm ISO 534

# Laminate

Total Caliper 139 µm±10% ISO 534

## Performance Data

Initial Tack 14 N/25mm FTM 9 Glass Peel Adhesion 90° 7.5 N/25mm FTM 2 St.St.

Min. Application Temp. -25 °C

Service Temperature -50 °C to 70 °C

# Adhesive Performance

The adhesive is specially designed for use at low temperature and freezer conditions. It features good tack and adhesion to a wide variety of packaging materials, such as paper, cardboard and films, including apolar, curved or irregular substrates. Generally good adhesion performance can even be achieved on slightly frosted surfaces.

# Applications and Use

The product is used in a variety of labelling applications, when the advantages of digital printing: short runs, last minute changes, personalised layouts and fast turn-round full colour printing are required.

# Conversion and Printing

This product is qualified for HP Indigo digital printing. It includes a topcoat designed for printing with HP Indigo presses, ensuring excellent ink anchorage and image quality, without the need of in-line priming. Print quality in conventional processes and combination with laquers to be tested. Very good conversion characteristics in rotary and flat-bed. It is recommended to overvarnish or overlaminate the product to protect the print for applications with high level of scratching.


# Compliance and Approvals

The adhesive C2075N is suitable for contact with dry, moist, and non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

# **BA007**

# Fasson ®

# DIG INDI PP TOP WHITE C2075N-BG45WH FSC



DIG INDI PP TOP WHITE

C2075N

BG45WH FSC



The mark of responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



Adhesive C2075N has attained the one star certification for biobased content according to EN 16640, meaning that C2075N contains certified Biobased Carbon Content of at least 20%. (TÜV AUSTRIA licensee number: S0259)



\*The OK biobased certification is only applicable to the adhesive C2075N.

# Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

# Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <a href="http://terms.europe.averydennison.com">http://terms.europe.averydennison.com</a>



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.