

### Facestock

A clear bi-axially oriented polypropylene film with a specific topcoating for excellent transfer and anchorage of ElectroInk as used in the Indigo process, allowing a wide range of design and performance choices on rigid packaging and bottles.

Basis Weight	52 g/m <sup>2</sup>	ISO 536
Caliper	57 µm	ISO 534

### Adhesive

A general purpose removable, acrylic based adhesive.

### Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	72 g/m <sup>2</sup>	ISO 536
Caliper	63 µm	ISO 534

### Laminate

Total Caliper	132 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	4 N/25mm	FTM 9 Glass
Peel Adhesion 90°	2 N/25mm	FTM 2 St.St.
Min. Application Temp.	-15 °C	
Service Temperature	-30 °C to 80 °C	

### Adhesive Performance

The adhesive features good tack and adhesion in combination with superior and clean removability from most substrates. Good UV resistance and long term removability. The adhesive allows label application at subzero temperatures and retains its removable properties over a wide temperature range.

### Applications and Use

The product is used in a variety of labelling applications, when the advantages of digital printing: short runs, last minute changes, personalised layouts and fast turn-round full colour printing are required.

R5000N removes clean from many substrates from polymeric (e.g. PET, PP, ABS), card and fibre board, aluminium, stainless steel or glass (not suitable for window labelling). The use of R5000N adhesive on certain types of cardboards, or recycled fibres can be critical and it is strongly recommended to proceed to application testing before use.

### Conversion and Printing

This product is qualified for HP Indigo digital printing. It includes a topcoat designed for printing with HP Indigo presses, ensuring excellent ink anchorage and image quality, without the need of in-line priming. Print quality in conventional processes and combination with laquers to be tested. Excellent conversion characteristics in rotary and flat-bed. It is recommended to overvarnish or overlamine the product to protect the print for applications with high level of scratching.

# BA019

## Fasson ®

### DIG INDI PP TOP CLEAR R5000N-BG45WH FSC



DIG INDI PP TOP CLEAR

R5000N

BG45WH FSC



The mark of  
responsible forestry

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Compliance and Approvals

The adhesive R5000N is suitable for contact with dry, moist, and fatty foodstuffs that have a reduction factor of 2 or higher in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

### Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.