

Facestock

A clear bi-axially oriented polypropylene film with a specific topcoating for excellent transfer and anchorage of ElectroInk as used in the Indigo process, allowing a wide range of design and performance choices on rigid packaging and bottles.

Basis Weight	52 g/m ²	ISO 536
Caliper	57 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

A clear polyester liner giving optimum smoothness to the adhesive layer. rPET30 liner contains 30% Post-Consumer Recycled (PCR) content. This liner is 100% recyclable. Visit our website for more information.

Basis Weight	42 g/m ²	ISO 536
Caliper	30 µm	ISO 534

Laminate

Total Caliper	105 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	9 N/25mm	FTM 9 Glass
Peel Adhesion 90°	7 N/25mm	FTM 2 St.St.
Min. Application Temp.	10 °C	
Service Temperature	-20 °C to 80 °C	

Adhesive Performance

S4000N is an extra clear, permanent adhesive featuring excellent UV, water and heat resistance and good tack and adhesion performance - even on apolar surfaces such as polyethylene bottles and packaging films. Used in combination with filmic liners.

Applications and Use

The product is used in a variety of labelling applications, when the advantages of digital printing: short runs, last minute changes, personalised layouts and fast turn-round full colour printing are required.

Automatic application: The robust film liner allows for consistent, snap free, application on high speed lines.


Conversion and Printing

This product is qualified for HP Indigo digital printing. It includes a topcoat designed for printing with HP Indigo presses, ensuring excellent ink anchorage and image quality, without the need of in-line priming. Print quality in conventional processes and combination with laquers to be tested. Excellent conversion characteristics in rotary and flat-bed. It is recommended to overvarnish or overlamine the product to protect the print for applications with high level of scratching.

BA020

Fasson ®

DIG INDI PP TOP CLEAR S4000N-rPET30



DIG INDI PP TOP CLEAR

S4000N

rPET30

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.
If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com*

As the liner is transparent, the applicator must detect the print itself or registration marks must be provided on either face or liner. Press stability is good with stable, consistent register during conversion. Flat bed performance is good while solid and magnetic rotary dies need additional care. (Die bearers must be adjusted to the polyester liner). The PCR content gives a transparent light blue/grey shade to the liner. This does not affect the performance; performance is on par with conventional PET liners.

Compliance and Approvals

The adhesive S4000N is suitable for contact with dry, moist and non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.