

#### Facestock

A gloss white polyester film. The smooth surface is print treated to achieve good TT printability and ink anchorage.

Basis Weight	71 g/m <sup>2</sup>	ISO 536
Caliper	50 µm	ISO 534

#### Adhesive

A special purpose rubber hotmelt adhesive, featuring high tack and final peel adhesion with very high coat weight.

#### Liner

BG45WH BSS: on both sides siliconized glassine paper, wood-free, super calendered and extremely tough and tear-resistant.

Basis Weight	72 g/m <sup>2</sup>	ISO 536
Caliper	63 µm	ISO 534
Transparency	45 %	DIN 53147

#### Laminate

Total Caliper	166 µm±10%	ISO 534
---------------	------------	---------

#### Performance Data

Initial Tack	40 N/25mm	FTM 9 glass FINAT FTM 9 (vidro)
Peel Adhesion 90°	23 N/25mm	FTM2 st.st. 20min
Min. Application Temp.	0 °C	
Service Temperature	-20 °C to 70 °C	

#### Adhesive Performance

TS8000 uses an aggressive formulation developed for labelling rubber with irregular and curved surfaces. It withstands typical chemicals used by tyre manufacturers, such as mould release agents or components migrating from the rubber.

#### Applications and Use

Transfer PET White PT is specifically developed for Durable Goods labelling. Typical examples are identification and warning labels on electronic devices and household appliances.

The main application for this material is tyre labelling for the production of point-of-purchase labels that are required to adhere to all-season and winter tyres in a reliable way. This label material does not have any negative effect on the properties and performance of labelled tyres. In addition it is also used in other applications in which a highly aggressive adhesive is needed to label rough surfaces.

Special care should be given during dispensing around the gum free area.

#### Conversion and Printing

The glossy, smooth surface is print treated and can be thermal transfer printed, the best results can be obtained with resin ribbons. It can be printed by all conventional print technologies. This material is qualified for UV inkjet printing by the following printer manufacturers: Domino (n610i), Durst (TAU 330 RSC) and Xeikon (PX3000). Results of durability tests are available on request.

## BC460

### Fasson ®

PET50 PT WHITE  
TS8000 DEC SGP-45WH BSS



TRANSFER PET WHITE PT

TS8000

BG45WH BSS

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

Note: this product contains a very aggressive adhesive. If the product is without SGP (Special Gum Pattern), adhesive ooze on the sides of the slit rolls can occur. To minimize this risk it is highly recommended to order this material with an adhesive-free zone on each side of the slit rolls (with SGP / gumpattern). Please contact your sales representative for further details.

The special product lay-out could have an influence on conversion speed.

#### Compliance and Approvals

Adhesive TS8000 has attained the two star certification for biobased content according to EN 16640, meaning that TS8000 contains certified Biobased Carbon Content of at least 40%. (TÜV AUSTRIA licensee number: S0259)



\*The OK biobased certification is only applicable to the adhesive TS8000.

#### Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

#### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.