

### Facestock

A white woodfree matt uncoated paper with a 'laid' textured surface; wet strength and fungicidal treatment. The rPLUS underlamine contains 70% post consumer recycled content (PCR), ensuring optimum performances in the ice bucket, and in wet conditions in general, by minimizing the risk of wrinkling of the material.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	123 g/m <sup>2</sup>	ISO 536
Caliper	146 µm	ISO 534

### Adhesive

A general purpose permanent, rubber based adhesive for the wine industry.

### Liner

A clear polyester liner giving optimum smoothness to the adhesive layer.

Basis Weight	42 g/m <sup>2</sup>	ISO 536
Caliper	30 µm	ISO 534

### Laminate

Total Caliper	192 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	23 N/25mm	FTM 9 Glass
Peel Adhesion 90°	12 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-30 °C to 70 °C	

### Adhesive Performance

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, and slightly rough substrates.

### Applications and Use

The product is suitable for primary labelling of high and luxury goods with an 'old world' image, e.g.: wines, spirits and specialist foods. Due to the high stiffness of the facestock we do not recommend this construction for small diameter substrates (neck label).

For optimal dispensing a relatively high tension on the backing and a sharp beak are recommended.

### Conversion and Printing

Printable by all conventional printing techniques. Due to open and textured nature of the facematerial, best results are in general from those techniques with maximum conformability of printing plate such as flexo and offset. Excellent results, in line with desired image, using offset or screen.

Press stability is good with stable, constant register during conversion. Flat bed performance is good while solid and magnetic rotary dies need additional care. (Die bearers must be adjusted to the polyester liner).

# BE074

## Fasson ®

### VERGE BLANC PLUS FSC S2047N-PET30



VERGE BLANC PLUS FSC

S2047N

PET30



*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Compliance and Approvals

The adhesive S2047N is suitable for contact with dry and moist, non-fatty foodstuffs. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

Adhesive S2047N has attained the two star certification for biobased content according to EN 16640, meaning that S2047N contains certified Biobased Carbon Content of at least 40%. (TÜV AUSTRIA licensee number: S0259)



\*The OK biobased certification is only applicable to the adhesive S2047N.

### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.