

Facestock

A white uncoated, matt, laid watermarked, woodfree printing paper with a tactile 'hand made' appearance and feel. Wet strength and fungicidal treatments.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	90 g/m ²	ISO 536
Caliper	122 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	72 g/m ²	ISO 536
Caliper	63 µm	ISO 534

Laminate

Total Caliper	205 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	17 N/25mm	FTM 9 Glass
Peel Adhesion 90°	7 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 60 °C	

Adhesive Performance

The adhesive features high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates. Specially designed for wine labelling applications it allows easy conversion of difficult label shapes. Engineered to help minimizing the loss of opacity in wet conditions (grey effect).

Applications and Use

This product is designed for Wine labelling, it is suitable for primary labelling of high and premium goods with an 'old world' image eg: spirits, specialist foods. Under wet conditions the facestock will turn grey making it less suitable for products exposed to the ice-bucket.

Conversion and Printing

Printable by all conventional printing techniques. Due to open and textured nature of the facematerial, best results are in general from those techniques with maximum conformability of printing plate such as flexo and offset. Excellent results, in line with desired image, using offset or screen.

Compliance and Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry, non fatty foodstuffs.

The laminate is made with FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

BJ106

Fasson®

VERGE BLANC FSC
Z1010-BG45WH FSC



VERGE BLANC FSC

Z1010

BG45WH FSC



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.