

Facestock

A white, high gloss, coated paper with a highly absorbent surface structure specifically designed for waterbased ink jet printing. Gives excellent colour reproduction and bright, vivid colours.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	88 g/m ²	ISO 536
Caliper	99 µm	ISO 534
CIE-whiteness D65	155 pts	ISO 11475

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG40 white, a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	57 g/m ²	ISO 536
Caliper	51 µm	ISO 534

Laminate

Total Caliper	170 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	17 N/25mm	FTM 9 Glass
Peel Adhesion 90°	7 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 60 °C	

Adhesive Performance

The adhesive features high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates. Specially designed for wine labelling applications it allows easy conversion of difficult label shapes. Engineered to help minimizing the loss of opacity in wet conditions (grey effect).

Applications and Use

The product is used in a variety of labelling applications, when the advantages of digital printing: short runs, last minute changes, personalised layouts and fast turnaround full colour printing are required.

- Quick drying and enhanced moisture resistance offer good handleability after printing.
- Glossy premium face paper for prestigious labels (gifts, cosmetics, special editions).
- Good barcode readability, high opacity, very good dot definition, excellent black printing quality.

Conversion and Printing

Compatible with OEM labelling equipment, such as Epson, Primera, Memjet and other water-based inkjet systems. Optimised for dye and pigment inks. In addition to Ink Jet the material can be printed by Thermal Transfer and conventional technologies; we recommend flexo for best results using low viscosity inks, the ink consumption may be high due to the nature of the paper. The material can be converted by roll-to-roll conversion technologies.

BQ338

Fasson ®

DEMAND JET GLOSS FSC Z1010-BG40WH FSC



DEMAND JET GLOSS FSC

Z1010

BG40WH FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Compliance and Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry, non fatty foodstuffs.

The laminate is made with FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.