

Facestock

A gloss, transparent, slightly hazy, corona treated, soft polyethylene cling film applied on a cast coated board liner. Ideal for labels that cling without adhesive on glossy surfaces, requiring easy removal of the label and without leaving any residue.

Basis Weight	236 g/m ²	ISO 536
Caliper	258 µm	ISO 534
Min. Application Temp.	5 °C	
Caliper (film only)	110 µm	T411
Density	0.925 gr/cc	ASTM D792
Weight (liner only)	135 g/m ²	ISO 536
Surface Tension	38 mN/m	measured with test inks
Service temp.	-20 to +50 °C	
Cling Adhesion	0.01 N/25mm	FTM1 on glass

Applications and Use

Fasson STATIC CLING PE CL-110PT clings without adhesive on smooth, glossy surfaces like glass, PET, PMMA and PC. It can be easily removed and leaves no residues. However, we do recommend that in combination with laquers and plastics the compatibility has to be tested. The product could be reused / reapplied.

Conversion and Printing

The product can be converted by conventional roll conversion technologies including: Screen, UV offset and UV flexo.

IMPORTANT NOTES:

- Due to the limited shelf life of this product we recommend to print the material immediately after delivery. The surface of the film may be marked by the back side of the release liner, due to time, temperature and roll length. For better gloss and transparency it is therefore recommended to use the material immediately.
- The Expected Life Time of the printed label is up to 2 years in indoor conditions.
- One minute after separation from backing paper the material shrinks in MD about - 2%; CD + 1%.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

BT941

Fasson ®

STATIC CLING PE CL-110PT



STATIC CLING PE CL-110PT

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2021 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.