

Facestock

A cavitated white bi-axially oriented, polypropylene film with a print-receptive topcoat.

Basis Weight 41 g/m 2 ISO 536 Caliper 57 μ m ISO 534

Adhesive

SR3011N is a wash off emulsion adhesive with general purpose conversion and application properties, designed to enable recycling of PET packages.

Liner

A clear polyester liner giving optimum smoothness to the adhesive layer. rPET23 liner contains 30% Post-Consumer Recycled (PCR) content. This liner is 100% recyclable. Visit our website for more information.

Basis Weight 32 g/m^2 ISO 536 Caliper $23 \text{ } \mu \text{m}$ ISO 534

Laminate

Total Caliper 93 µm±10% ISO 534

Performance Data

Initial Tack 10 N/25mm FTM 9 glass

FINAT FTM 9

(vidro)

Peel Adhesion 90° 5.5 N/25mm FTM 2 st.st.

24hr

Min. Application Temp. 5 °C

Service Temperature -20 °C to 50 °C

Adhesive Performance

SR3011N CleanFlake™ adhesive is designed for labeling and recycling of PET bottles and PET containers. SR3011N labels adhere to the PET package until the very end of its life cycle, when at the recycler the label+adhesive release cleanly from the PET bottle, in a hot caustic water bath. SR3011N is releasing from the PET but still adhering to the face material, allowing the label and adhesive to cleanly separate from the PET flakes.* No residual adhesive remains in the water or on the PET flakes which could contaminate, discolor, or otherwise diminish the rPET value. This new proprietary adhesive exhibits excellent converting and dispensing characteristics.

* For sink/float separation and compliance with recycling regulations, the adhesive must be combined with a face material with a density <1kg/cm3.

Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film, we recommend additional testing prior to use on non-uniform surfaces and where a level of squeezability is desired.

Typical applications for SR3011N are in beverage, food, home and personal care market segments where PET bottles and PET containers are used.


The adhesive is designed for application on a dry package. For consistent, snap free application on high speed lines, we recommend combining the adhesive with a rPET liner.

Automatic application: The robust film liner allows for consistent, snap free application on high speed lines.

BX550

Fasson ®

CLEANFLAKE WHITE SR3011N-rPET23



PP60 CAVIT TOP WHITE

SR3011N

rPET23

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com



Conversion and Printing

The topcoated film can be printed by conventional and digital printing techniques such as UV flexo, UV Inkjet, screen, offset, letterpress, gravure and hot or cold foiling processes. The topcoat is designed for optimal ink adhesion with UV-cured inks, including low migration inks, and is compatible with LED curing systems. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. On-press corona treatment is not advised. The material has very good register properties especially when a high number of different colors are used.

As the liner is transparent, the applicator must detect the print itself or registration marks must be provided on either face or liner. Press stability is good with stable, consistent register during conversion. Flat bed performance is good while solid and magnetic rotary dies need additional care. (Die bearers must be adjusted to the polyester liner). The PCR content gives a transparent light blue/grey shade to the liner. This does not affect the performance; performance is on par with conventional PET liners.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.