

### Facestock

A white bi-axially oriented, polypropylene film with a print-receptive topcoat.

Basis Weight	39 g/m <sup>2</sup>	ISO 536
Caliper	47 µm	ISO 534

### Adhesive

CleanFlake™: A clear wash-off general purpose acrylic adhesive with excellent conversion and application properties.

### Liner

BG40WH FSC, a supercalandered siliconized white glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	57 g/m <sup>2</sup>	ISO 536
Caliper	51 µm	ISO 534

### Laminate

Total Caliper	110 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	9 N/25mm	FTM 9 glass FINAT FTM 9 (vidro)
Peel Adhesion 90°	5.5 N/25mm	FTM2 st.st. 20min
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 50 °C	

### Adhesive Performance

S7000ER enables recyclability of rigid plastic packaging (HDPE, PET). It applies and functions as a permanent adhesive when applied on glass, PET, HDPE, PP, metal. At the end of life of the HDPE or PET package S7000ER labels are designed not to hinder the recycling. The adhesive exhibits a balance of release properties to enable high speed converting and dispensing on increasingly thinner substrates. Excellent wet out and water whitening resistance. Significantly less adhesive bleed vs. industry standard, including in a tropical environment, which reduces downtime on press and dispensing equipment.

Care and additional testing is recommended for use in multi-layer booklet applications on small diameter packages.

### Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film, care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired. Application in: food, home and personal care, cosmetics, beverages.


Application on: glass, PET, HDPE, PP, metal. Application on dry surfaces.

Enables recycling: PET, HDPE

## CH990

## Fasson®

### CLEANFLAKE PP50 WHITE S7000ER-BG40WH FSC



PP50 TOP WHITE

S7000ER

BG40WH FSC



*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Conversion and Printing

The topcoated film can be printed by conventional and digital printing techniques such as UV flexo, UV Inkjet, screen, offset, letterpress, gravure, letterpress and hot or cold foiling processes. The topcoat is designed for optimal ink adhesion with UV-cured inks, including low migration inks, and is compatible with LED curing systems. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. On-press corona treatment is not advised. The material has very good register properties especially when a high number of different colors are used.

### Compliance and Approvals

The adhesive S7000ER is suitable for contact with dry, moist and fatty foodstuffs with reduction factor of 4 or higher in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

S7000ER in combination with polyolefin face materials (PE, PP, Global MDO) is approved by Recyclclass as fully compatible with the rigid HDPE recycling stream.

S7000ER in combination with face materials with density  $<1\text{g/cm}^3$  (label+ink+varnish) is enabling recyclability of PET packages:

- following Petcore guidance for PET trays and packages ( $>70^\circ\text{C}$ )
- EPBP recognition for PET bottle recycling ( $>80^\circ\text{C}$ )

### Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.